

6128

UNDERBODY COATING –SATIN CLEAR

KATS 6128 is a high solids version of 6028 to improve coverage and dry time, and a water based rust preventive coating that is formulated utilizing plant base polymer technology to provide outstanding protection against corrosion on both ferrous and nonferrous metals. The product is colorless (clear) and leaves at attractive satin finish. The normal duration of protection is up to 3 years.

KATS 6128 is approved by GM Brazil based on the internal study per GM9984190 specification for underbody use.

KATS 6128 is not meant for application where yellowing resistance is critical.

KATS 6128 can be applied using an airless sprayer or automatic spray systems. The application area should be sheltered from rain and excessive wind.

Ambient/Surface Temperature..... 45° - 100°F (7° - 38°C)
 Ideal Surface Temperature 60° - 80°F (16° - 27°C)
 Note: Insure the coating is dry before exposing to the elements.

Wet Film Thickness ... 3.8 - 7.7 mil (96.5 - 195.6 microns)
 Dry Film Thickness 1 - 2 mil (25.4 - 50.8 microns)

Typical Coverage..... 208 - 416 ft²/gal (5.1 - 10.2 m²/l)

Agitate before and during use.

BENEFITS:

- 0.8 lb/gal (96 gm/liter) VOC
- HAPs-free
- Excellent adhesion to various substrates
- Protects outdoors up to 3 years
- Quick drying
- Contains no oil or petroleum
- No fire hazard
- Early water resistance
- Environmentally safe

APPLICATIONS:

Use KATS 6128 to prevent rust and corrosion on metal surfaces. Typical applications include:

- Vehicle underbody coating
- Protection of machine components during storage
- Protection of metal stock
- Protection of outdoor stored gears

Note: The dried film may turn slightly yellow/amber in tone over time, depending on the conditions.

TEST METHOD	DESCRIPTION	TYPICAL CHARACTERISTIC
ASTM D-2347	Humidity Exposure	Passed 500 hours with less than 0.01% surface rust
GM 9508P	Gravelometer (tests impact protection)	Pass
ASTM B-117	Salt Spray Test	Passed at 50 hours exposure with less than 0.01% surface corrosion
ASTM D-2243	Freeze and Thaw Stability, Cycles Passed	3
ASTM D-2196 Modified	Brookfield Viscometer Spindle #4 @ 72°F (22°C) and 60 RPM, cps	3,000 - 10,000
ASTM D-1475	Density	8.8 lb/gal (1.056 g/cm ³)

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

PACKAGING

260 Gallon Totes	55 Gallon Drums	5 Gallon Pails
------------------	-----------------	----------------

A Division of **The Whitmore Manufacturing Company**

930 Whitmore Drive • P.O. Box 9300 • Rockwall, Texas 75087 • USA • (972) 771-1000 • Fax: (972) 722-2108
 An ISO 9001, ISO/TS 16949, and ISO 14001 Registered Company • www.katscoatings.com

LIMITED WARRANTY: The Whitmore Manufacturing Company makes the Limited Express Warranty that at the date of delivery, its goods shall be free from defects in Whitmore's materials and workmanship and shall meet the express written statements of quality, if any, made by Whitmore in connection with the sale of the goods. Other than such Limited Express Warranty, there are no express warranties made with respect to the sale of goods and all implied warranties existing under the law are expressly disclaimed and negated, particularly, Whitmore NEGATES AND DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. All other liability, either in contract or tort, including without limitation, strict liability found in Section 402A of the Restatement of Torts or otherwise, is negated and disclaimed. The sole remedy for Whitmore's breach of such Limited Express Warranty shall be a refund of the purchase price of its goods, and Whitmore shall have no responsibility for incidental or consequential damages sustained as a result of the use of the goods, whether sustained to the goods themselves or to other property. Data listed are subject to usual manufacturing variations.