

9600 OPC SERIES

PEELABLE COATING

KATS 9600 OPC (Outdoor Premium Coating) is a series of temporary peelable coatings designed to protect outdoor surfaces from abrasion and unwanted contaminants. KATS 9600 OPC products contain no volatile organic compounds.

KATS 9600 OPC can be sprayed onto non-porous surfaces. When dry, the coating can be manually peeled from the surface equally well in hot or cold weather.

KATS 9600 OPC will give maximum coverage and film thickness in a single coat. When sprayed on, the film builds quickly, creating a suitable film in fewer passes.

Ambient/Surface Temperature..... 45° - 100°F (7° - 38°C)
 Ideal Surface Temperature 60° - 80°F (16° - 27°C)
 Atmosphere Low humidity

Spray Gun Airless (water compatible)
 Air Pressure 1500 - 2000 psi (103.4 - 137.9 bar)

Wet Film Thickness 4 - 8 mil (101.6 - 203.2 microns)
 Dry Film Thickness 2 - 4 mil (50.8 - 101.6 microns)

Typical coverage..... 200 - 400 ft²/gal (4.9 - 9.8 m²/l)

Mix before using and do not allow fluid to freeze.

BENEFITS:

- Zero VOC
- A cost-effective alternative to plastic film
- Coating peels easily in both hot and cold weather
- Excellent protection from abrasion and contamination
- Tough, yet flexible film
- Water based
- No offensive odor
- Environmentally friendly

APPLICATIONS:

Use KATS 9600 OPC for protection of painted surface, galvanized metal, plastic, and glass surfaces.

- Vehicles
- Machine tools
- Farm equipment
- Industrial work-in-process (stored outdoors)
- Windows (Use KATS 9601 IPC-Clear during home construction)

Note: We recommend running a compatibility test before using KATS 9600 OPC extensively.

TEST METHOD	DESCRIPTION	TYPICAL CHARACTERISTIC		
		9601 OPC-Clear	9602 OPC-White	9603 OPC-Blue
N/A	Appearance (Virgin)	Off White	Off White	Pastel Blue
N/A	Appearance (Dried Film)	Semitransparent	Off White	Opaque Pastel Blue
ASTM D-1475	Density	8.7 lb/gal (1.04 g/cm ³)	8.9 lb/gal (1.07 g/cm ³)	8.9 lb/gal (1.07 g/cm ³)
ASTM D-2196 Modified	Brookfield Viscometer Spindle 4 @ 60 rpm @ 72°F (22°C)	2000 – 6000 cps		

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

PACKAGING

260 Gallon Totes	55 Gallon Drums	5 Gallon Pails
---------------------	--------------------	-------------------

A Division of **The Whitmore Manufacturing Company**

930 Whitmore Drive • P.O. Box 9300 • Rockwall, Texas 75087 • USA • (972) 771-1000 • Fax: (972) 722-2108
 An ISO 9001, ISO/TS 16949, and ISO 14001 Registered Company • www.katscoatings.com

LIMITED WARRANTY: The Whitmore Manufacturing Company makes the Limited Express Warranty that at the date of delivery, its goods shall be free from defects in Whitmore's materials and workmanship and shall meet the express written statements of quality, if any, made by Whitmore in connection with the sale of the goods. Other than such Limited Express Warranty, there are no express warranties made with respect to the sale of goods and all implied warranties existing under the law are expressly disclaimed and negated, particularly, Whitmore NEGATES AND DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. All other liability, either in contract or tort, including without limitation, strict liability found in Section 402A of the Restatement of Torts or otherwise, is negated and disclaimed. The sole remedy for Whitmore's breach of such Limited Express Warranty shall be a refund of the purchase price of its goods, and Whitmore shall have no responsibility for incidental or consequential damages sustained as a result of the use of the goods, whether sustained to the goods themselves or to other property. Data listed are subject to usual manufacturing variations.