

4550

Zero VOC Clear

KATS 4550 is a colorless, water based indoor/covered outdoor rust preventive coating that is free of volatile organic compounds. It protects ferrous and nonferrous metals and can be applied over light rust. Protection lasts up to 12 months, depending on storage conditions. It can be applied using a manual spray wand or an automatic system.

KATS 4550 is white when applied. As it dries the coating changes and takes on an attractive clear gloss that seals the metal and repels water.

The surfaces to be protected should be clean and dry. Apply KATS 4550 in a good ventilated area without excessive wind. Before using, review MSDS and wear proper gear.

KATS 4550 can be applied using a water-compatible HVLP, automatic, or manual spray system. HVLP is recommended due to its transfer efficiency.

Ambient/Surface Temperature..... 70° - 100°F (21° - 38°C)

Ideal Surface Temperature 70° - 90°F (21° - 32°C)

Note: Insure the coating is dry before exposing to the elements. To minimize temperature/humidity variables, heated force drying is recommended to improve early water resistance.

Wet Film Thickness ... 2.5 mil (63.5 microns)

Dry Film Thickness 0.5 mil (12.7 microns)

Typical Coverage..... 640 ft²/gal (16 m²/l)

Do not allow fluid to freeze.

BENEFITS:

- Zero VOC
- Excellent adhesion to various surfaces
- Excellent humidity resistance
- Repels water
- Excellent yellowing resistance
- Protects up to 12 months
- Quick drying
- No fire hazard
- Environmentally safe

APPLICATIONS:

KATS 4550 is designed to protect engine or other ferrous and non-ferrous metal for indoor/covered outdoor storage.

TEST METHOD	DESCRIPTION	TYPICAL CHARACTERISTIC
ASTM D-2247	Humidity Chamber Test	Passed 1000 hours with less than 0.01% surface rust
ASTM B-117	Salt Spray Test	Passed 50 hours with less than 0.01% surface rust
ASTM D-3359	Adhesion Test (Q panel CRS)	5B
ASTM D-2196	Viscosity Brookfield Viscometer DV-I spindle #4 @ 100 rpm @ 72°F	300 - 600 cps
ASTM D-1475	Density	8.45 .b/gal (1.01 g/cm ³)

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

PACKAGING

260 Gallon Totes	55 Gallon Drums	5 Gallon Pails
---------------------	--------------------	-------------------

A Division of Whitmore

930 Whitmore Drive • Rockwall, Texas 75087 • USA • (972) 771-1000 • 1-800-699-6318

An ISO 9001 and ISO 14001 registered company • www.katscoatings.com

LIMITED WARRANTY: The Whitmore Manufacturing Company makes the Limited Express Warranty that at the date of delivery, its goods shall be free from defects in Whitmore's materials and workmanship and shall meet the express written statements of quality, if any, made by Whitmore in connection with the sale of the goods. Other than such Limited Express Warranty, there are no express warranties made with respect to the sale of goods and all implied warranties existing under the law are expressly disclaimed and negated, particularly, Whitmore NEGATES AND DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. All other liability, either in contract or tort, including without limitation, strict liability found in Section 402A of the Restatement of Torts or otherwise, is negated and disclaimed. The sole remedy for Whitmore's breach of such Limited Express Warranty shall be a refund of the purchase price of its goods, and Whitmore shall have no responsibility for incidental or consequential damages sustained as a result of the use of the goods, whether sustained to the goods themselves or to other property. Data listed are subject to usual manufacturing variations.